

Window Putty

Product properties

Flügger Window putty is an oil-based putty with ready-to-use texture.

- Ready-to-use oil-based putty
- Good adhesion on wood and glass
- Used for puttying of windows



Product use

Use indoors and outdoors for puttying of windows and filling of minor holes in woodwork.

Must be coated after drying.

Substrate

Must be clean, dry, solid and suitable for surface treatment.

Treatment

Clean, sand, and remove loose material and paint.

Remove dirt, grime, grease and chalking materials by cleaning.

New absorbent, porous or discoloured substrates are primed.

Apply the putty and smooth out.

Can be painted over as soon as the film has reached a sufficient thickness.

Should be painted over 1–2 mm inwards from the edge of the glass.

Application

Apply with a filler gun.

Cut off the tip of the sealant gun.

Cut the tip at an angle to adjust to Easily workable, press into place and smooth using a sealer squeegee or joint stick and water before the joint forms a skin.

Choose a tool based on the width of the joint.

Remove excess sealant mechanically.

Apply sealing tape if necessary and remove it immediately after application.

Cold/ heat can affect the viscosity of the material.

Condensation must not occur.

Always perform a test treatment for a check and acceptance of adhesion and result.

Expected result

Even surface for additional treatment.

Environmental information

Remove as much sealant as possible from your tools before cleaning.

Do not pour leftover sealant down the drain; take it to your local recycling centre.

Minimise your paint waste by calculating in advance how much you will need.

Store any leftover sealant correctly so that it can be reused, thereby minimising the environmental impact.

Storage

Cool, frost-free, and tightly closed

Supplementary Info

Shelf life: 24 months in unopened container.

Technical Data

Product Type	Plaster & Sealant
Density (kgs/l)	2.1
Min. working temp. during application and drying/curing	Min. +5°C
Humidity	Max. humidity 80 % RH.
Dry to touch at 20° C, 60 % RH (Hours)	48
Fully cured at 20° C, 60 % RH (Days)	28
Volume Shrinkage (%)	15
Cleaning of Tools etc.	White spirit
Country of Origin	Sweden

Current TDS Version

September 2026

Replaces TDS Version

May 2024