Interior High Finish 5 Classic

Product properties



Solvent-based alkyd enamel for the treatment of wood and metal indoors. The product is easy to apply, has excellent blocking properties, and provides a surface with an enamel-like finish. Recommended for areas with aesthetic and medium-functional requirements.

- **Good blocking properties**
- **Primer, undercoat and finishing paint**
- **Matt surface**

Product use

Primer, undercoat and finish treatment of wood or undercoating on previously treated or corrosion-protected iron and metal indoors.

Substrate

Must be clean, dry, solid and suitable for paint treatment.

Treatment

Remove loose material and paint by cleaning and sanding.
Remove dirt, filth, grease and chalking material with Fluren 37.
Hard, smooth substrates must be sanded matt.
Cracks, unevenness and holes must be filled.
New or bare cleaned wood must be primed.
Apply 1-2 coats. Some colours require additional treatments.

Application

Brush, roller or spray
Choose appropriate tools for the desired finish
Apply wet-on-wet, and finish by brushing/rolling in the same direction
Always use the same batch number for continuous/unbroken surfaces
Differences in surface texture may result in shade deviations
Cold or heat can affect the material’s viscosity
Material temperature when spraying must be min. 12 °C.
Condensation must not form during drying/curing
Cold weather and high atmospheric humidity extend the drying time, complete curing and re-coat interval
High temperature and low atmospheric humidity reduce the drying time and complete curing
Always apply test treatments to check and accept the adhesion and results

Expected result
Matt surface.
Good coalescence.
Withstands ordinary soiling, use-related wear and cleaning with universal detergent, a soft brush, water and a cloth.
Strong, especially dark shades are more delicate than light colours by wear and touch.
Chalking due to surplus pigment may occur.
Treat the surface with caution until the paint is fully cured.

Please note!
Cloths with the product can self-ignite.
Should be saturated with water or destroyed after use.

Environmental information
Minimize your paint waste by pre-estimating how much paint you need.
Remove as much paint as possible from tools before cleaning.
Paint and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.
Empty and dry packaging should be sorted as metal.
Store excess paint correctly so that leftovers can be used and environmental impact is minimised.

Storage
Cool, frost-free and tightly closed

Protection equipment
Protect skin and eyes from splashes with suitable clothing, gloves and glasses.
Avoid inhalation of spray mist and grinding dust.
Wear suitable protective equipment, see safety data sheet for further information.

Technical Data

Product Type	Alkyd oil paint
Gloss	5;Matte
Density (kgs/l)	1,57
Solids Weight %	76
Solids Vol. %	53
Nominal spreading rate (m²/ltr.)	6
Min. working temp. during application and drying/curing	Min. +5°C
Humidity	Max. humidity 80 % RH.
Dry to touch at 20° C, 60 % RH (Hours)	6
Recoat interval at 20° C, 60 % RH (Hours)	48
Fully cured at 20° C, 60 % RH (Days)	28
Washability acc. to EN-13300/ISO-11998	Class 1
Dilution	Do not diluted
Cleaning of Tools etc.	White spirit
Country of Origin	Sweden

Current TDS Version

June 2026

Replaces TDS Version

April 2025