Filler Perform P

Product properties

High-pressure spray filler for dry rooms. Contains fine-grained material with medium weight, good filling capacity and high strength. Finish treatment with a wall covering and/or suitable ceiling or wall paint in the desired colour and gloss.



- **Multi-filler**
- **High tensile strength**
- **Light grey**

Labelling

Product use

Filling when smoothing out on plaster, concrete, lightweight concrete and previously painted surfaces.
Filling and reinforcing of joints with Flügger approved CE labelled gypsum tape and filling screw holes on gypsum plasterboard.

Substrate

Must be clean, dry, firm and suitable for surface treatment.

Treatment

Remove loose material and paint by cleaning, sanding and dusting.
Remove dirt, grime, grease and chalking materials by cleaning with Fluren 37.
Water-soluble discolouration, nicotine and soot can be cleaned with Fluren 49.
Sand flat hard, slippery surfaces.
Apply the filler paste and smooth out.
Can be used for structural spraying of ceilings without additional treatment.
Dust off and fill the gypsum board joints and place the plaster tape with the prefabricated fold against the joint, pressing firmly with the knife and pressing down into the wet filler paste.
Press the tape in so far that a thin layer of filler paste is deposited on the outside of the tape.
At the same time, scrape the filler over the tape.
Once it has dried, fill the joints and screw holes twice.
Sand the surface and prime it before any additional treatment.

Application
Apply using a special spray system and smooth out with a filler knife.
Decide your choice of tools based on the size of the surface.
Min. +10°C for the air, material and substrate during application, drying and curing.
For spray application, the nozzle, filter and spray equipment must be adjusted to suit the product and the task.
Check the operation of the spray equipment regularly, and clean the filter, spray gun and nozzle as required to ensure optimal operation and an even result.
Apply a sufficient amount, work and smooth the filler.
Cold/ heat can affect the viscosity of the material.
Condensation during drying/curing must not form.
Cold and increased humidity extends drying time, full curing and recoating interval.
Increased temperature and low atmospheric humidity reduce drying time and full curing.
Risk of shrinkage where the filler paste is not completely cured before additional treatment.
Always perform a test application to check and approve adhesion and the result.

Expected result
Even surface for additional treatment.

Please note!
Install the gypsum board according to the manufacturer’s instructions and standards.
See the Flügger user directions for gypsum board, filling of joints.

Environmental information
Minimize your paint waste by pre-estimating how much filler you need.
Remove as much filler as possible from tools before cleaning.
Filler and cleaning fluid must not be poured down drains, but collected and disposed of as environmental waste.
Empty and dry packaging should be sorted as plastic, metal handles should be removed and sorted as metal.
Store excess filler correctly so that leftovers can be used and environmental impact is minimised.

Storage
Store in a cool, frost-free place with the container tightly closed.
Recommended storage temperature: +5°C to +30°C.
The product must be allowed to reach the working temperature before use.

Protection equipment
Protect skin and eyes from splashes with suitable clothing, gloves and glasses.
Avoid inhalation of spray mist and grinding dust.
Wear suitable protective equipment, see safety data sheet for further information.

Supplementary Info
The product meets the requirements of M1: Emission Classification of Building Materials: Protocol for Chemical and Sensory Testing of Building Materials.

Technical Data

Product Type	Plaster & Sealant
Color (plaster)	Light grey
Density (kgs/l)	1.41
Solids Weight %	65
Solids Vol. %	50
Min. working temp. during application and drying/curing	Min. +10°C
Humidity	Max. humidity 80 % RH.
Recoat interval at 20° C, 60 % RH (Hours)	16
Adhesion on concrete (MPa)	0.64
Layer thickness (nominal mm)	2
Grain size (max. Mm)	0.25
Cleaning of Tools etc.	Water
Country of Origin	Sweden

Current TDS Version

October 2026

Replaces TDS Version

June 2026